

## ***Grey waterproofing slurry***

- *waterproofing against active or passive water pressure*
- *for concrete and masonry*
- *efflorescence-free*
- *applicable by spray equipment*
- *suitable also for corrosion protection for reinforcing steel*
- *approved for potable water*

---

### **PRODUCT DESCRIPTION**

Vandex BB 75 is a cementitious, ready-mixed surface waterproofer. It is also suitable as corrosion protection for reinforcing steel.

### **AREAS OF APPLICATION**

- substrate: concrete and masonry
- active or passive waterproofing and protection against water and moisture
- foundations, slabs, retaining walls, etc.
- drinking water structures
- corrosion protection for reinforcing steel

### **PROPERTIES**

Owing to its composition of cement, quarts with graded grain-size distribution and selected additives, Vandex BB 75 is waterproof. It can be employed against active and passive water pressures. The initial and final bonding capability of Vandex BB 75 is excellent, making it suitable to be applied to horizontal as well as vertical surfaces. It is durable, resistant to frost and heat after setting, but all the same permeable to vapour. Vandex BB 75 is tested for use in contact with drinking water.

Applied as corrosion protection, it does not only enhance rebar corrosion protection, but also improves adhesion to subsequently applied Vandex repair and coating mortar. It forms a hard coating, is resistant to frost and de-icing salts, allows vapour diffusion and reduces CO<sub>2</sub> penetration.

### **SURFACE PREPARATION**

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance have to be removed by suitable means. Water leaks must be stopped e.g. with Vandex Plug. Thoroughly moisten the substrate, it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

#### Brick- and blockwork substrates:

Any remaining plaster, render or other substances that could inhibit bonding must be removed back to the substrate. Gypsum, remains of wood or other foreign material must be removed by appropriate means. Loose pointing must be routed out and the substrate cleaned thoroughly.

#### For application as corrosion protection:

Exposed reinforcing steel should be cleaned and the residue removed by sandblasting or by using other suitable tools (be sure to achieve Sa2½ clean rating in accordance with DIN EN 12944-4 resp. ISO 8501-1). Remove concrete surrounding the corroded steel to a sound substrate. Steel and concrete may be moist.

### **MIXING**

Mix 25kg of Vandex BB 75 with 4.5 to 6 litres of tap water in a clean container for at least 3 minutes to a lump-free homogenous consistency. Use a mechanical mixer.

### **APPLICATION**

Vandex BB 75 is applied with brush, trowel or suitable spray equipment. A maximum of 2mm (approx. 4kg/m<sup>2</sup>) can be applied in one working cycle. In most cases the application of more than one coat is recommended; please refer to relevant specification. It is recommended to apply the next coat whilst the previous coat is still damp on the surface. The previous coat must not be damaged during application of the following coat. The waiting time before applying the following coat depends on local climatic conditions such as humidity, temperature, etc. The previous coat is textured by suitable means whilst still plastic to form a key. To maintain workability of the material, do not add water, simply re-stir the mixture.

#### Brush application:

Ensure that all cavities in the substrate are filled.

#### Trowel application:

First a scratch coat is applied for maximum adhesion to the substrate, working from the bottom up. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

#### Spray application:

Vandex BB 75 can be applied with a suitable fine mortar spraying device. For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 6mm. The first layer of Vandex is applied in a circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened and keyed. The final layer can be left as a spray finish or treated to a specified finish.

#### Application as corrosion protection:

Using brush or roller, carefully apply at least two coats of Vandex BB 75 with no breaks on prepared steel. Each subsequent coat may be applied after about 1 hour on sufficiently hardened first coat. Depending on temperature, use within 45 to 60 minutes.

Do not apply at temperatures below +5°C, or to a frozen substrate.

### **CURING**

Keep damp for at least 5 days and provide suitable protection against extreme weather conditions (e.g. sun, wind, frost) while setting. The freshly treated surfaces should be protected from rain for a minimum period of 24 hours.

### **PLASTERING/COATING**

Surfaces treated with Vandex products which are to be coated or painted should be left to cure for at least 28 days. When a plaster or render finish is required on top of a Vandex treatment, it is essential to apply a rough cast of sand and cement on the final Vandex coat while it is still tacky. On hardened Vandex surfaces apply an appropriate bonding agent before rendering. Coatings on top of a Vandex treatment have to be alkali resistant. Decorative coatings applied on the passive water pressure site are recommended to be water vapour permeable.

### **CONSUMPTION**

#### **Waterproofing**

TYPE OF WATER IMPACT	RECOMMENDED OVERALL APPLICATION RATE	NUMBER OF LAYERS
Pressureless water	3 to 4kg/m <sup>2</sup>	1.5 to 2mm
Water under pressure	4 to 6kg/m <sup>2</sup> , depending on water pressure	2 to 3mm

#### **Corrosion protection:**

Approx. 2kg/m<sup>2</sup> per layer

#### Note:

Substrate and application conditions have to be observed. Depending on surface roughness, consumption may vary.

### **YIELD**

Approximate yield of a full kit, once mixed, is 14 litres.

### **TECHNICAL DATA**

Appearance	Grey powder
Density of wet mix (kg/l)	Approx. 2.0
Workability at 20°C (min)	Approx. 45
Setting time at 20°C (h)	Approx. 5 to 8
Compressive strength 28 days (MPa)	Approx. 40
Bending tensile strength 28 days (MPa)	Approx. 6
Static modulus of elasticity 28 days (GPa)	Approx. 28
Capillary absorption (kg/m <sup>2</sup> h <sup>0.5</sup> )	0.06

All data is averages of several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity and porosity of substrate may affect these values.

### **PACKAGING**

25kg lined paper bag

### **STORAGE**

When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

### **HEALTH AND SAFETY**

Vandex BB 75 contains cement. Irritating to respiratory system and skin. Risk of serious damage to eyes. Keep out of reach of children. Do not breathe dust. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Wear suitable gloves and eye / face protection. If swallowed, seek medical advice immediately and show this container or label. Provide good ventilation if handling bigger quantities or in enclosed areas. For more information, please refer to the actual Safety Data Sheet for Vandex BB75 and Vandex Cemelast Liquid.